



# 320 C CORNICE ADHESIVE

A Premium formula, with excellent initial adhesion strength that is **utilized in assembly of the polystyrene cornice sheets**. Also provides good performance with plasterboards and decoration materials.

## FEATURES & BENEFITS

- Initial adhesion ability of 120 kg/m<sup>2</sup>,
- Both vertical and horizontal application,
- Good gap-filling capacity on rough surfaces,
- Waterborne,
- No odor & solvent,
- Paintable.

## APPLICATIONS

- For assembly of the polystyrene decorative cornices and panels,
- Suitable for the substrates such as ceramic tiles, bricks, foams, felts etc.
- For the adhesion of plasterboards and ornamental materials,
- For the adhesion of the wooden construction elements.

## INSTRUCTIONS

- The substrates to be assembled must be flat, dry, dust-free and not have any traces of grease or other contaminants that could adversely affect the bonding performance.
- For fast curing and bonding, at least one of the surfaces should be porous.
- The application temperature should be between 5°C and 35 °C.
- Apply the adhesive on the edges and corners of the materials to be bonded and fix them in needed position within 10 minutes.
- Before the full curing surfaces can be moved and this gives time to users for desired application.
- Pressing can be necessary for full curing.
- During the curing, protect the materials from excessive moisture, water and rain.
- Adhesive can be fully cleaned with water before the cure.

Utilized in  
Assembly of the  
Polystyrene  
Cornice Sheets



## RESTRICTIONS;

- Not suitable for areas which are constantly exposed to water.
- The curing process may be retarded when both surfaces in contact are porous.
- The pressure applied in the beginning is critical to final bonding strength.

## STORAGE AND SHELF LIFE;

15 months between 5 and 25 °C in closed original packaging.

## PROPERTIES

<b>Basis</b>	: <b>Acrylic dispersion</b>	
<b>Density</b>	: : 1.70 ± 0.03 gr/cm <sup>3</sup>	(ASTM D 1875)
<b>Tack-Free Time</b>	: 30-40 minutes (at 25 °C and %50 R.H.)	(ASTM C 679)
<b>Curing Rate</b>	: 1-2 mm/day (at 25 °C and %50 R.H.)	
<b>Temperature Resistance</b>	: -10°C to +80°C	
<b>Application Temperature</b>	: +5°C to +40°C	
<b>Maximum Shear Strength (beech-beech)</b>		
<b>After 6 hours</b>	: > 25 kgf/cm <sup>2</sup>	
<b>After 24 hours</b>	: > 50 kgf/cm <sup>2</sup>	

## PRODUCT

Product Type	Volume	Package
320C ( Cartridge)	310 mL	12

## DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.